



DYES
for
Leather

by  **Softer Color**

catalog

ECONOMY

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it



ECONOMY

DYES FOR LEATHER by SOFTER COLOR

Softer Color, with more than 30 years of experience in the field, is the leader in the production and sale of a wide range of dyes for all industrial sectors, including the tanneries market.

We are therefore pleased to introduce our new leather catalog.

Our range of colors is made up of

- **Beige:** Researched to obtain various pastel shades
- **Penetration:** chosen for high penetration
- **Economy :** Studied to get a high value strength - price
- **Wet blue:** metal complex recommended for a high quality leather (prem)
- **Metal free:** recommended for a high quality leather (no prem)

Our wide range of dyestuffs offer concrete solutions for all our customers located in Europe, North Africa and America.

Through the creation of the right internal synergy, Softer Color takes care of its employees' health through high standards of safety and quality of work as well as the surrounding environment through the ISO 9001: 2015 certification; also shows a particular interest in social responsibility through the REACH registration of the products marketed.

information on solidity

LIGHT FASTNESS	I.U.F. 402
PENETRATION	I.M.
MIGRATION PVC	I.U.F. 442
EXHAUSTION	I.M.
SOLUBILITY GR/L 60° C	I.U.F. 201
FASTNESS TO WASHING	I.U.F. 423
FASTNESS TO PERSPIRATION	I.U.F. 426
FASTNESS TO ACID	I.U.F. 202
FASTNESS TO ALKALIS	I.M.
TROPICAL TEST	I.M.

Responsibility

Softer Color declines any responsibility for incorrect or improper use of its dyes. These products are not toxic, but it is very important to respect the safety rules provided by the attached SDS.

For any questions, please contact us at +39 0543 724672.





SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
							PERSPIRATION	ACID	ALKALIS	
YELLOW R ECO										
3% 	2	3/4	5	4	60	3	4	4/5	4/5	2/3
										
HAVANA BH										
3% 	3/4	2/3	5	5	70	4	4	4/5	4	5
										





SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST	
							PERSPIRATION	ACID	ALKALIS		
ORANGE 3R											
3%		3	2	4	3	40	4/5	5	4	2	4
											
BROWN G2R											
3%		2/3	2	4/5	2/3	60	4	4	5	3	4/5
											

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST	
							PERSPIRATION	ACID	ALKALIS		
RED R											
3%		1	3/4	4	4	40	2	3/4	4	4	2
											
BORDEAUX IBN											
3%		2/3	3/4	4/5	4/5	40	2/3	3/4	4/5	4/5	2
											

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it



DYES for *Leather*

by  **Softer Color**



ECONOMY

LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
						PERSPIRATION	ACID	ALKALIS	

BRILLANT BLUE 6B ECO

3%		1	2	4/5	4	20	1	2/3	4/5	3/4	2
											

DARK BLUE N

3%		1/2	3	4	4	40	3	4	5	5	2
											



SOFTER COLOR SRL



Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST	
							PERSPIRATION	ACID	ALKALIS		
OLIVE G ECO											
3%											
		2/3	3/4	4/5	4/5	60	3/4	4	4	4	4

OLIVE 2GN ECO											
3%											
		1/2	2	4	3	50	4	4	4	4	2



SOFTER COLOR SRL



Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
							PERSPIRATION	ACID	ALKALIS	
BROWN G ECO										
3% 	3/4	4	4/5	4	80	5	4	5	5	4/5
										

BROWN HG ECO										
3% 	1	3/4	4/5	4	80	4	5	5	4	5
										




SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
							PERSPIRATION	ACID	ALKALIS	
BROWN CG										
3%										
	3	2/3	5	3/4	50	4	4	5	3	5
BROWN HB										
3%										
	3	2	4	3	20	3	3	3	5	2



SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST	
							PERSPIRATION	ACID	ALKALIS		
BROWN NR ECO											
3%		3	3/4	3/4	4	50	4/5	4	4/5	4	2/3
BROWN DGV ECO											
3%		3	3	5	4	100	3	4	4/5	4	5





SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST	
							PERSPIRATION	ACID	ALKALIS		
BROWN SG ECO											
3%		3	3	1/2	3/4	50	2/3	2	3/4	2/3	1/2
											
BROWN MBL											
3%		2/3	3	5	5	70	4	4	4	4	5
											





SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it

DYES for *Leather*

by  **Softer Color**

ECONOMY

	LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
							PERSPIRATION	ACID	ALKALIS	
GREY W ECO										
3%		3	4/5	5	5	100	4	4	5	3
										
GREY BG										
3%		2/3	2	2	3/4	40	4/5	4/5	5	5
										

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it



DYES for *Leather*

by  **Softer Color**



ECONOMY

LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
						PERSPIRATION	ACID	ALKALIS	

BLACK BR ECO

3%		4	3	4/5	3/4	70	3/4	3/4	5	5	4
											

BLACK T400

3%		2/3	4	4/5	4/5	60	4	4	4	3/4	2/3
											

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it


DYES for *Leather*

by  **Softer Color**

ECONOMY

BLACK VEG

3%



LIGHT FASTNESS	PENETRATION	MIGRATION PVC	EXHAUSTION	SOLUBILITY GR/L 60° C	WASHING	FASTNESS TO			TROPICAL TEST
						PERSPIRATION	ACID	ALKALIS	
2/3	4	4/5	4	30	3/4	3/4	3	4	4

SOFTER COLOR SRL

Via Golfarelli, 88/D
47122 Forlì - Italia
Tel. +39.0543.724672
Fax +39.0543.724650
info@softercolor.it
www.softercolor.it